

CE 0766 B

Product Information

CE 0766 B is a High Performance, multi-purpose polyurethane designed for processing through plural component, high pressure or low pressure dispensing equipment. Once fully cured, it is tough yet flexible with high impact and tear resistance along with excellent chemical and water resistance. CE 0766 B performs well as Rock Climbing Holds etc....

Physical Properties (Components)

	Component A	Component B
Viscosity at 75°F (cps)	160 - 200	600 - 900
Specific Gravity (gr/ml)	1.22 - 1.24	1.01 - 1.02

Physical Properties (Final Product)

Hardness, Shore D, ASTM D-2240	63 - 67
Tensile Strength (psi), ASTM D-412	N/A
Elongation (%), ASTM D-412	N/A
Flexural Strength ASTM D-790	N/A
Color	Natural

Handling Characteristics

Mix by Weight (A/B)	37 / 63
Gel Time at 75°F (seconds)	270 - 300
Demold Time (min)	15 - 25
90% Cure Time (hours)	24

Storage and Shelf Life

Components should be kept well sealed in a dry place from 70 to 90°F. Shelf life of unopened containers is six (6) months from manufacturing date. Mix Component B well prior to each use. Purge opened containers with dry nitrogen before resealing. Refer to product SDS for more information.

Packaging

Component A:	5 gallon pails	38 lb	Net Weight
	55 gallon steel drum (closed top)	500 lb	Net Weight
	275 gallon plastic totes	2500 lb	Net Weight
Component B:	5 gallon pails	38 lb	Net Weight
	55 gallon steel drum (open top)	450 lb	Net Weight
	275 gallon plastic totes	2250 lb	Net Weight

Non-Warranty: This information is furnished without warranty, expressed or implied, except that is accurate to the best knowledge of Eteco, Inc. The data on these sheets relates only to the specific material designated herein. Eteco, Inc. assumes no legal responsibility for use or reliance upon this data. The user should conduct sufficient investigation to establish the suitability of any product for its intended use.