



1000 South Linwood Avenue, Santa Ana, CA 92705
Phone: (714) 480-1370, Fax: (714) 558-1990

Date: 8/23/18

CG 601-7 A

Product Information

CG 601-7 A is an MDI based single component moisture curable adhesive designed for variety of application where strong and impact resistant bond is required. CG 601-7 A is excellent choice for wood to wood and polyurethane foam to wood bonding.

Physical Properties (Components)

Component A

Viscosity at 75°F (cps)
Specific Gravity (gr/ml)

500 - 800
1.11 - 1.13

Physical Properties (Final Product)

Hardness, Shore A, ASTM D-2240
Tensile Strength (psi), ASTM D-412
Elongation (%), ASTM D-412
Tear Strength (pli)
Color

40 - 60
1800
200
110
Opaque White

Handling Characteristics

Gel Time at 75°F (minutes)
Tack Free Time (minutes)
90% Cure Time (hours)

6 - 9
10
24

Storage and Shelf Life

Components should be kept well sealed in a dry place from 70 to 90°F. Shelf life of unopened containers is six (6) months from manufacturing date. Mix Component B well prior to each use. Purge opened containers with dry nitrogen before resealing. Refer to product SDS for more information.

Packaging

Component A:	55 gallon steel drum (closed top)	490 lb	Net Weight
--------------	-----------------------------------	--------	------------

Non-Warranty: This information is furnished without warranty, expressed or implied, except that is accurate to the best knowledge of Eteco, Inc. The data on these sheets relates only to the specific material designated herein. Eteco, Inc. assumes no legal responsibility for use or reliance upon this data. The user should conduct sufficient investigation to establish the suitability of any product for its intended use.