



1000 South Linwood Avenue, Santa Ana, CA 92705
Phone: (714) 480-1370, Fax: (714) 558-1990

Date: 11/21/18

CG 603-7 A

Product Information

CG 603-7A is a versatile single component moisture cure 100% polyurethane adhesive that is sandable, paintable and stainable. CG 603-7A can be applied by roller, brush or trowel. CG 603-7A is temperature resistant and water resistant and exhibits excellent adhesion to primed metal, wood, polyurethane foam, ceramic and concrete.

Physical Properties (Components)

	Component A
Viscosity at 75°F (cps)	3000 - 3500
Specific Gravity (gr/ml)	1.10 - 1.12

Handling Characteristics

Gel Time at 75°F (minutes)	6 - 9
Tack Free Time (minutes)	10
90% Cure Time (hours)	24
Color	Opaque White

Installation Recommendations

CG 603-7A is fully formulated and ready for use. Product temperature can be ambient during application onto substrates that are free of loose particles, oil, grease, dirt, etc. Apply one coat by brush, roller or trowel.

Application rate is 250 – 350 square feet per gallon depending on substrate porosity and profile. Concrete Surface Prep using Abrasive Blast per SSPC 13.

Storage and Shelf Life

Components should be kept well sealed in a dry place from 70 to 90°F. Shelf life of unopened containers is six (6) months from manufacturing date. Mix Component B well prior to each use. Purge opened containers with dry nitrogen before resealing. Refer to product SDS for more information.

Packaging

Component A:	55 gallon steel drum (closed top)	490 lb	Net Weight
--------------	-----------------------------------	--------	------------

Non-Warranty: This information is furnished without warranty, expressed or implied, except that is accurate to the best knowledge of Eteco, Inc. The data on these sheets relates only to the specific material designated herein. Eteco, Inc. assumes no legal responsibility for use or reliance upon this data. The user should conduct sufficient investigation to establish the suitability of any product for its intended use.