

## F7806 Black

### Product Information

F7806 Black is a high performance I - Skin flexible polyurethane foam designed for processing through plural component low or high-pressure dispensing equipment. Once fully cured, this material is tough, flexible with excellent physical properties. F7806 Black is designed for use in applications where tough skin is required with good memory and with excellent mechanical properties strength. F7806 Black could be used for such applications as, Fitness Equipment pads, Bolster gaming pads, Arm Rest etc...

### Physical Properties (Components)

	Component A	Component B
Viscosity at 75°F (cps)	400 - 600	200 - 300
Specific Gravity (gr/ml)	1.09 - 1.12	1.01 - 1.02

### Physical Properties (Final Product)

Tensile Strength (psi), ASTM D-638	290
Elongation (%), ASTM D-638	335
Tear Strength (pli), ASTM D1004	45
Shore A	55 - 60
Color	Black

### Handling Characteristics

Mix Ratio by Weight (Component A/Component B)	37 / 63 to 42 / 58
Mix Ratio by Volume (Component A/Component B)	N/A
Cream Time (sec)	23 - 28
Rise Time (sec)	85 - 95
Tack Free Time (sec)	85 - 110
Demold Time (minutes)	4 - 6
Final Cure Time (hours)	24
Density (pcf)	5.0 - 6.0

### Storage and Shelf Life

Components A and B should be kept well sealed in a dry place at a temperature from 75°-90°F. Shelf life of unopened containers is six (6) months from manufacturing date. Purge opened containers with dry nitrogen before resealing. Premix component B prior to use. Refer to product SDS for more information.

### Packaging

Component A:	55 gallon steel drum (closed top)	500 lbs	Net Weight
Component B:	55 gallon steel drum (open top)	440 lbs	Net Weight

**Non-Warranty:** This information is furnished without warranty, expressed or implied, except that is accurate to the best knowledge of Eteco, Inc. The data on these sheets relates only to the specific material designated herein. Eteco, Inc. assumes no legal responsibility for use or reliance upon this data. The user should conduct sufficient investigation to establish the suitability of any product for its intended use.