



**Product Information**

CG 601-07 A is an MDI based single component moisture curable adhesive designed for a variety of applications where a strong and impact resistant bond is required. CG 601-07 A is an excellent choice for wood to wood and polyurethane foam to wood bonding.

Physical Properties (Final Product)	Units	Test Method	Results
Color	-	Visual	Opaque White

Handling Characteristics	Units	Component A
Specific Gravity @ 75°F	g/mL	1.11 - 1.13
Viscosity @ 75°F	cPs	500 - 800
Color	Visual	Pale Yellow
Gel Time @ 75°F	Minutes	6 - 9
Tack Free Time	Minutes	10
90% Cure Time*	Hours	24

\*Final properties will be reached in a course of several days. Properties are typical and not for specifications\*

**Installation Recommendations**

CG 601-07 A is fully formulated and ready for use. Product temperature can be ambient during application onto substrates that are free of loose particles, oil, grease, dirt, etc. Apply one coat by brush, roller, or towel.

Application rate is 250-350 sqft. per gallon depending on substrate porosity and profile. Prepare concrete surface using Abrasive Blast per SSPC 13.

**Storage and Shelf Life**

Components should be kept well sealed in a dry place from 70 to 90°F. Shelf life of unopened containers is six (6) months from manufacturing date. Mix Component B well prior to each use. Purge opened containers with dry nitrogen before resealing. Refer to product SDS for more information.

**Packaging**

Component A: 55 gallon steel drum (closed top) 490 lb Net Weight

For more information contact Eteco, Inc. (714) 480-1370 | [info@etecoinc.com](mailto:info@etecoinc.com)  
[www.etecoinc.com](http://www.etecoinc.com)

**Non-Warranty:** This information is furnished without warranty, expressed or implied, except that is accurate to the best knowledge of Eteco, Inc. The data on these sheets relates only to the specific material designated herein. Eteco, Inc. assumes no legal responsibility for use or reliance upon this data. The user should conduct sufficient investigation to establish the suitability of any product for its intended use.

