

## FT 7474-6 TECHNICAL DATA SHEET

Flexible Foam Polyurethane System



## **Product Information**

FT 7474-6 is a high performance, Semi flexible polyurethane foam designed for processing through plural component low or high-pressure dispensing equipment. Once fully cured, this material is tough and flexible. FT 7474-6 is designed for use in Archery Foam applications where self healing properties are required in addition too good memory and with excellent tear strength.

| Physical Properties (Final Product) | Units | Test Method   | Results           |
|-------------------------------------|-------|---------------|-------------------|
| Free Rise Density                   | pcf   | ASTM D1622-03 | 5.5 - 6.5         |
| Compressive Strength                | %     | ASTM D-1621   | -                 |
| Tensile Strength                    | psi   | ASTM D-412    | -                 |
| Elongation                          | %     | ASTM D-412    | -                 |
| Tear Strength                       | pli   | ASTM D-1004   | 20                |
| Color                               | -     | Visual        | Natural/Pigmented |

| Handling Characteristics | Units   | Component A | Component B      |
|--------------------------|---------|-------------|------------------|
| Mix Ratio by Volume      | (A/B)   | -           | -                |
| Mix Ratio by Weight      | (A/B)   | 44          | 56               |
| Specific Gravity @ 75°F  | g/mL    | 1.14 - 1.16 | 1.01 - 1.03      |
| Viscocity @ 75°F         | cPs     | 550 - 750   | 700 - 800        |
| Color                    | -       | Amber       | Opaque/White-ish |
| Cream Time @ 75°F        | Seconds | 45          | - 55             |
| Rise Time                | Seconds | 230 - 260   |                  |
| Tack Free Time           | Seconds | 280 - 320   |                  |
| Demold Time              | Minutes | 10          | - 45             |
| Final Cure Time          | Hours   | 24          |                  |

<sup>\*</sup> The density and processing times listed are derived from a statistical average of long-term testing. We recommend a test mix be performed before use. Eteco, Inc. quality control tests and product packaging are based on the Mix Ratio by Weight \*

## Storage and Shelf Life

Components should be kept well sealed in a dry place from 70 to 90°F. Shelf life of unopened containers is six (6) months from manufacturing date. Mix Component B well prior to each use. Purge opened containers with dry nitrogen before resealing. Refer to product SDS for more information.

**Packaging** 

Component A: 55 gallon steel drum (closed top) 500 lb Net Weight

275 gallon plastic totes 2500 lb Net Weight

Component B: 55 gallon steel drum (open top) 450 lb Net Weight

275 gallon plastic totes 2250 lb Net Weight

**Non-Warranty**: This information is furnished without warranty, expressed or implied, except that is accurate to the best knowledge of Eteco, Inc. The data on these sheets relates only to the specific material designated herein. Eteco, Inc. assumes no legal responsibility for use or reliance upon this data. The user should conduct sufficient investigation to establish the suitability of any product for its intended use.