

## HLS 8505 TECHNICAL DATA SHEET

Rigid Foam Polyurethane System



## **Product Information**

HLS 8505 is a High Performance, rigid polyurethane foam designed for processing through plural component, low or high pressure dispensing equipment or mixing and pouring by hand. Once fully cured, this material is tough with high compression and tensile value. HLS 8505 exhibits very good surface characteristics and excellent moldability.

| Physical Properties (Final Product) | Units | Test Method | Results   |
|-------------------------------------|-------|-------------|-----------|
| Free Rise Density                   | pcf   | ASTM D-1622 | 5.0 - 5.5 |
| Compressive Strength                | psi   | ASTM D-1621 | -         |
| Tensile Strength                    | psi   | ASTM D-1623 | -         |
| Shear Strength                      | psi   | ASTM D-273  | -         |
| Elongation                          | %     | ASTM D-1623 | 3         |
| Tear Strength                       | pli   | ASTM D-624  | -         |

| Handling Characteristics | Units   | Component A | Component B |
|--------------------------|---------|-------------|-------------|
| Mix Ratio by Volume      | (A/B)   | -           | -           |
| Mix Ratio by Weight      | (A/B)   | 50          | 50          |
| Specific Gravity @ 75°F  | g/mL    | 1.21 - 1.23 | 1.18 - 1.20 |
| Viscocity @ 75°F         | cPs     | 200 - 250   | 900 - 1000  |
| Color                    | -       | Amber       | Amber       |
| Cream Time @ 75°F        | Seconds | 40 - 50     |             |
| Gel Time @ 75°F          | Seconds | 160 - 180   |             |
| Rise Time                | Seconds | 200 - 250   |             |
| Tack Free Time           | Seconds | 220 - 270   |             |
| Demold Time              | Minutes | 10 - 45     |             |
| Final Cure Time          | Hours   | 24          |             |

<sup>\*</sup>Properties are typical and not for specifications\*

## Storage and Shelf Life

Components should be kept well sealed in a dry place from 70 to 90°F. Shelf life of unopened containers is six (6) months from manufacturing date. Mix Component B well prior to each use. Purge opened containers with dry nitrogen before resealing. Refer to product SDS for more information.

## **Packaging**

Component B:

Component A: 55 gallon steel drum (closed top) 500 lb Net Weight

275 gallon plastic totes 2500 lb Net Weight 55 gallon steel drum (open top) 450 lb Net Weight

275 gallon plastic totes 2250 lb Net Weight

For more information contact Eteco, Inc. (714) 480-1370 | info@etecoinc.com www.etecoinc.com

Non-Warranty: This information is furnished without warranty, expressed or implied, except that is accurate to the best knowledge of Eteco, Inc. The data on these sheets relates only to the specific material designated herein. Eteco, Inc. assumes no legal responsibility for use or reliance upon this data. The user should conduct sufficient investigation to establish the suitability of any product for its intended use.