



Product Information

HP 8206 is a medium density rigid polyurethane molding foam system designed for processing through plural component dispensing equipment. Once fully cured, this material is tough with high compression and tensile value. HP 8206 exhibits very good surface characteristics and excellent moldability. This product is recommended for molding intricate decorative simulated wood furniture parts, moldings, picture frames and other decorative parts. This material is Eco Friendly due to its lack of HCFC's, HFC's, and lead or other heavy metals.

Physical Properties (Final Product)	Units	Test Method	Results
Free Rise Density	pcf	ASTM D-1622	5.8 - 6.2
Compressive Strength	psi	ASTM D-1621	80
Tensile Strength	psi	ASTM D-1623	-
Shear Strength	psi	ASTM D-273	65
Elongation	%	ASTM D-1623	-
Closed Cell Content	%	ASTM D-2856	-

Handling Characteristics	Units	Component A	Component B
Mix Ratio by Volume	(A/B)	50	50
Mix Ratio by Weight	(A/B)	52	48
Specific Gravity @ 75°F	g/mL	1.21 - 1.23	1.07 - 1.09
Viscosity @ 75°F	cPs	150 - 250	500 - 700
Color	-	Amber	Opaque/Beige-ish
Cream Time @ 75°F	Seconds	55 - 65	
Gel Time @ 75°F	Seconds	90 - 120	
Rise Time	Seconds	120 - 160	
Tack Free Time	Seconds	160 - 220	
Demold Time	Minutes	15 - 30	
Final Cure Time	Hours	24	

Properties are typical and not for specifications

Storage and Shelf Life

Components should be kept well sealed in a dry place from 70 to 90°F. Shelf life of unopened containers is six (6) months from manufacturing date. Mix Component B well prior to each use. Purge opened containers with dry nitrogen before resealing. Refer to product SDS for more information.

Packaging

Component A:	55 gallon steel drum (closed top)	500 lb Net Weight
	275 gallon plastic totes	2500 lb Net Weight
Component B:	55 gallon steel drum (open top)	450 lb Net Weight
	275 gallon plastic totes	2250 lb Net Weight

For more information contact Etenco, Inc. (714) 480-1370 | info@etecoinc.com
www.etecoinc.com

Non-Warranty: This information is furnished without warranty, expressed or implied, except that is accurate to the best knowledge of Etenco, Inc. The data on these sheets relates only to the specific material designated herein. Etenco, Inc. assumes no legal responsibility for use or reliance upon this data. The user should conduct sufficient investigation to establish the suitability of any product for its intended use.