



Product Information

RS 1404 is a two-component CFC, HCFC and HFC free polyurethane foam designed for spray in place applications. This formulation is recommended where thermal insulation, structural integrity and environmentally friendly efficient products are required. RS 1404 spray in place foam system shall be applied in half inch passes or less, maximum 1 inch passes, using standard plural component polyurethane foam high pressure, impingement mix temperature controlled equipment.

Physical Properties (Final Product)	Units	Test Method	Results
Free Rise Density	pcf	ASTM D-1622-03	3.5 - 4.5
Compressive Strength	psi	ASTM D-1620	75
Tensile Strength	psi	ASTM D-1623	100
K-Factor	BTU-in/hr-ft ² -°F	ASTM C-177	0.18 - 0.20
Closed Cell Content	%	ASTM D-1940	> 93%

Handling Characteristics	Units	Component A	Component B
Mix Ratio by Volume	(A/B)	50	50
Mix Ratio by Weight	(A/B)	52	48
Specific Gravity @ 75°F	g/mL	1.22 - 1.24	1.04 - 1.07
Viscosity @ 75°F	cPs	180 - 220	600 - 800
Color	-	Amber	Beige
Cream Time @ 75°F	Seconds	3 - 4	
Rise Time	Seconds	10 - 12	
Tack Free Time	Seconds	18 - 22	
Final Cure Time	Hours	24	

Properties are typical and not for specifications

Storage and Shelf Life

Components should be kept well sealed in a dry place from 70 to 90°F. Shelf life of unopened containers is six (6) months from manufacturing date. Mix Component B well prior to each use. Purge opened containers with dry nitrogen before resealing. Refer to product SDS for more information.

Packaging

Component A:	55 gallon steel drum (closed top)	500 lb Net Weight
	275 gallon plastic totes	2500 lb Net Weight
Component B:	55 gallon steel drum (open top)	450 lb Net Weight
	275 gallon plastic totes	2250 lb Net Weight

For more information contact Eteco, Inc. (714) 480-1370 | info@etecoinc.com
www.etecoinc.com

Non-Warranty: This information is furnished without warranty, expressed or implied, except that is accurate to the best knowledge of Eteco, Inc. The data on these sheets relates only to the specific material designated herein. Eteco, Inc. assumes no legal responsibility for use or reliance upon this data. The user should conduct sufficient investigation to establish the suitability of any product for its intended use.